

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
10.750	32.75	H-40	840	1820	1820			205			367	0.279	10.192	10.036	
10.750	40.50	H-40	1390	2280	2280			314			457	0.350	10.050	9.894	
10.750	40.50	J-55	1580	3130	3130		3130	420		700	629	0.350	10.050	9.894	
10.750	40.50	K-55	1580	3130	3130		3130	450		819	629	0.350	10.050	9.894	
10.750	40.50	HCK-55	2100	3130	3130		3130	562		911	629	0.350	10.050	9.894	
10.750	40.50	N-80	1730	4560	4560		4560	597		964	915	0.350	10.050	9.894	
10.750	40.50	HCN-80	2100	4560	4560		4560	681		1034	915	0.350	10.050	9.894	
10.750	45.50	J-55	2090	3580	3580		3580	493		796	715	0.400	9.950	9.794	9.875
10.750	45.50	K-55	2090	3580	3580		3580	528		931	715	0.400	9.950	9.794	9.875
10.750	45.50	HCK-55	3130	3580	3580		3580	659		1037	715	0.400	9.950	9.794	9.875
10.750	45.50	N-80	2470	5210	5210		5210	701		1097	1040	0.400	9.950	9.794	9.875
10.750	45.50	HCN-80	3130	5210	5210		5210	799		1175	1040	0.400	9.950	9.794	9.875
10.750	51.00	J-55	2700	4030	4030		4030	565		891	801	0.450	9.850	9.694	
10.750	51.00	K-55	2700	4030	4030		4030	606		1043	801	0.450	9.850	9.694	
10.750	51.00	HCK-55	4420	4030	4030		4030	756		1160	801	0.450	9.850	9.694	
10.750	51.00	L-80	3220	5860	5860		5860	794		1190	1165	0.450	9.850	9.694	
10.750	51.00	HCL-80	4460	5860	5860		5860	906		1316	1165	0.450	9.850	9.694	
10.750	51.00	N-80	3220	5860	5860		5860	804		1228	1165	0.450	9.850	9.694	
10.750	51.00	HCN-80	4460	5860	5860		5860	916		1316	1165	0.450	9.850	9.694	
10.750	51.00	C-90	3400	6590	6590		6590	879		1287	1311	0.450	9.850	9.694	
10.750	51.00	H2S-90	4460	6590	6590		6590	916		1316	1311	0.450	9.850	9.694	
10.750	51.00	S-95	4460	6960	6960		6960	937		1392	1383	0.450	9.850	9.694	
10.750	51.00	T-95	3480	6960	6960		6960	927		1354	1383	0.450	9.850	9.694	
10.750	51.00	H2S-95	4460	6960	6960		6960	927		1354	1383	0.450	9.850	9.694	
10.750	51.00	C-95	3480	6960	6960		6960	927		1354	1383	0.450	9.850	9.694	
10.750	51.00	HCP-110	4460	8060	8060		8060	1080		1594	1602	0.450	9.850	9.694	
10.750	51.00	P-110	3660	8060	8060		8060	1080		1594	1602	0.450	9.850	9.694	
10.750	51.00	HCQ-125	4660	9160	9160		9160	1213		1758	1820	0.450	9.850	9.694	
10.750	51.00	Q-125	3740	9160	9160		9160	1213		1758	1820	0.450	9.850	9.694	
10.750	55.50	HCK-55	5220	4430	4430		4430	843		1271	877	0.495	9.760	9.604	9.625
10.750	55.50	L-80	4020	6450	6450		6450	884		1303	1276	0.495	9.760	9.604	9.625
10.750	55.50	HCL-80	5950	6450	6450		6450	1010		1441	1276	0.495	9.760	9.604	9.625
10.750	55.50	N-80	4020	6450	6450		6450	895		1345	1276	0.495	9.760	9.604	9.625
10.750	55.50	HCN-80	5950	6450	6450		6450	1021		1441	1276	0.495	9.760	9.604	9.625
10.750	55.50	C-90	4160	7250	7250		7250	979		1409	1435	0.495	9.760	9.604	9.625
10.750	55.50	H2S-90	5950	7250	7250		7250	1021		1441	1435	0.495	9.760	9.604	9.625
10.750	55.50	S-95	5950	7660	7660		7660	1043		1524	1515	0.495	9.760	9.604	9.625
10.750	55.50	T-95	4290	7660	7660		7660	1032		1483	1515	0.495	9.760	9.604	
10.750	55.50	H2S-95	5950	7660	7660		7660	1032		1483	1515	0.495	9.760	9.604	9.625
10.750	55.50	C-95	4290	7660	7660		7660	1032		1483	1515	0.495	9.760	9.604	9.625
10.750	55.50	HCP-110	5950	8860	8860		8860	1203		1745	1754	0.495	9.760	9.604	9.625
10.750	55.50	P-110	4610	8860	8860		8860	1203		1745	1754	0.495	9.760	9.604	9.625

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
10.750	55.50	HCQ-125	5950	10070	10070		10070	1351		1925	1993	0.495	9.760	9.604	9.625
10.750	55.50	Q-125	4850	10070	10070		10070	1351		1925	1993	0.495	9.760	9.604	9.625
10.750	60.70	L-80	5160	7100	7100		7100	983		1428	1398	0.545	9.660	9.504	
10.750	60.70	HCL-80	7550	7100	7100		7100	1123		1579	1398	0.545	9.660	9.504	
10.750	60.70	N-80	5160	7100	7100		7100	996		1473	1398	0.545	9.660	9.504	
10.750	60.70	N-80	5160	7100	7100		7100	996		1473	1398	0.545	9.660	9.504	
10.750	60.70	HCN-80	7550	7100	7100		7100	1136		1579	1398	0.545	9.660	9.504	
10.750	60.70	C-90	5460	7980	7980		7980	1089		1544	1573	0.545	9.660	9.504	
10.750	60.70	H2S-90	7550	7980	7980		7980	1136		1579	1573	0.545	9.660	9.504	
10.750	60.70	S-95	7550	8430	8430		8430	1161		1670	1660	0.545	9.660	9.504	
10.750	60.70	T-95	5590	8430	8430		8430	1148		1625	1660	0.545	9.660	9.504	
10.750	60.70	H2S-95	7550	8430	8430		8430	1148		1625	1660	0.545	9.660	9.504	
10.750	60.70	C-95	5590	8430	8430		8430	1148		1625	1660	0.545	9.660	9.504	
10.750	60.70	HCP-110	7550	9760	9760		9760	1338		1912	1922	0.545	9.660	9.504	
10.750	60.70	P-110	5880	9760	9760		9760	1338		1912	1922	0.545	9.660	9.504	
10.750	60.70	HCQ-125	7550	11090	11090		11090	1503		2109	2184	0.545	9.660	9.504	
10.750	60.70	Q-125	6070	11090	11090		11090	1503		2109	2184	0.545	9.660	9.504	
10.750	65.70	L-80	6300	7750	7750		7750	1082		1551	1519	0.595	9.560	9.404	9.504
10.750	65.70	HCL-80	8640	7750	7750		7750	1236		1716	1519	0.595	9.560	9.404	9.504
10.750	65.70	N-80	6300	7750	7750		7750	1096		1600	1519	0.595	9.560	9.404	9.504
10.750	65.70	HCN-80	8640	7750	7750		7750	1249		1716	1519	0.595	9.560	9.404	9.504
10.750	65.70	C-90	6760	8720	8720		8720	1198		1677	1708	0.595	9.560	9.404	
10.750	65.70	H2S-90	8640	8720	8720		8720	1249		1716	1708	0.595	9.560	9.404	9.504
10.750	65.70	S-95	8640	9200	9200		9200	1277		1814	1803	0.595	9.560	9.404	9.504
10.750	65.70	T-95	6960	9200	9200		9200	1263		1765	1803	0.595	9.560	9.404	
10.750	65.70	H2S-95	8640	9200	9200		9200	1263		1765	1803	0.595	9.560	9.404	9.504
10.750	65.70	C-95	6960	9200	9200		9200	1263		1765	1803	0.595	9.560	9.404	9.504
10.750	65.70	HCP-110	8640	10650	10650		10650	1472		2077	2088	0.595	9.560	9.404	9.504
10.750	65.70	P-110	7500	10650	10650		10650	1472		2077	2088	0.595	9.560	9.404	9.504
10.750	65.70	HCQ-125	8640	12110	12110		12110	1653		2291	2373	0.595	9.560	9.404	9.504
10.750	65.70	Q-125	7920	12110	12110		12110	1653		2291	2373	0.595	9.560	9.404	9.504
10.750	65.70	V-150	8320	14530	14530		14530	1978		2730	2847	0.595	9.560	9.404	9.504
10.750	71.10	H2S-90	9300	9520	9200		8980	1317		1822	1856	0.650	9.450	9.294	
10.750	71.10	S-95	9600	10050	9710		9480	1403		1971	1959	0.650	9.450	9.294	
10.750	71.10	H2S-95	9600	10050	9710		9480	1388		1918	1959	0.650	9.450	9.294	
10.750	71.10	HCP-110	9600	11640	11240		10980	1618		2257	2269	0.650	9.450	9.294	
10.750	71.10	P-110	9300	11640	11240		10980	1618		2257	2269	0.650	9.450	9.294	
10.750	71.10	Q-125	9990	13230	12780		12480	1817		2489	2578	0.650	9.450	9.294	
10.750	71.10	V-150	10880	15870	15330		14970	2174		2966	3094	0.650	9.450	9.294	
10.750	73.20	C-90	8760	9850							1915	0.672	9.406	9.250	

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
10.750	73.20	T-95	9090	10390							2021	0.672	9.406	9.250	
10.750	79.20	C-90	10370	10750							2079	0.734	9.282	9.126	
10.750	79.20	T-95	10800	11350							2194	0.734	9.282	9.126	
10.750	85.30	C-90	12010	11680							2243	0.797	9.156	9.000	
10.750	85.30	T-95	12540	12330							2367	0.797	9.156	9.000	